

Part Number: 9595424402

95 EER CORE SET

EER cores, similar to ETD cores, have been designed to make optimum use of a given volume of ferrite material for maximum throughput power. The structure, which includes a round center post, approaches a nearly uniform cross-sectional area throughout the core and provides a winding area that minimizes winding losses.

EER cores can be supplied with the center post gapped to a mechanical dimension or an A_L value.

Weight indicated is per pair or set.

Weight: 96 (g)

| Dim | mm | mm tol | nominal inch | inch misc. |
|-----|------|--------|--------------|------------|
| A | 42 | ± 0.70 | 1.654 | — |
| B | 22 | ± 0.20 | 0.866 | — |
| C | 15.2 | ± 0.35 | 0.598 | — |
| D | 15.4 | ± 0.20 | 0.606 | — |
| E | 30.5 | min | 1.201 | min |
| F | 15.2 | ± 0.35 | 0.598 | — |

Chart Legend

$\Sigma l/A$: Core Constant, l_e : Effective Path Length, A_e : Effective Cross-Sectional Area, V_e : Effective Core Volume

A_L : Inductance Factor 

Explanation of Part Numbers: Digits 1 & 2 = product class and 3 & 4 = material grade.

| Electrical Properties | |
|----------------------------------|-----------|
| A_L (nH) | 5900 ±25% |
| A_e (cm ²) | 1.87 |
| $\Sigma l/A$ (cm ⁻¹) | 5.2 |
| l_e (cm) | 9.79 |
| V_e (cm ³) | 18.26 |
| A_{min} (cm ²) | 1.81 |

A_L value is measured at 1 kHz, $B < 10$ gauss.

Fair-Rite Products Corp. • One Commercial Row, Wallkill, New York 12589-0288
888-324-7748 • 845-895-2055 • Fax: 845-895-2629 • ferrites@fair-rite.com • www.fair-rite.com